

GALVANIZED STEEL CABLE

ables Cadenas



s de México S.A. de C.V.

Size in Inches	Approx. Wt. per 1000 ft in pounds	Breaking Strength in Pounds*
1/16	7.5	480
5/64	11.0	650
3/32	16.0	920
1/8	28.0	1,700
5/32	43.0	2,600
3/16	62.0	3,700
1/4	106.0	6,100



Size in Inches	Approx. Wt. per 1000 ft in pounds	Breaking Strength in Pounds*	
3/32	17.4	1,000	
1/8	29.0	2,000	
5/32	45.0	2,800	
3/16	65.0	4,200	
7/32	86.0	5,600	
1/4 110.0		7,000	
5/16 173.0		9,800	
3/8	243.0 14,400		

Small diameter 7x7 and 7x19 construction cable is sometimes referred to as "aircraft cable". It is not intended for aircraft use but designed for industrial and marine applications according to Federal Specification RR-W-410, current revision and A.S.T.M. A 1023/A 1023M, as applicable

VENTAS@CCBM.MX +52 1 833227 8507

*Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength

WWW.CCBM.MX




CABLE-LAID WIRE ROPE

Galvanized.

Preformed To Be Used For Mechanically Swaged Slings Only. Do Not Use For Hand-spliced Assemblies Or For General Purpose Operating Rope.

Diameter Inches	Construction	Approx. Wt. per Foot. in Pounds	Breaking Strength in Tons*
3/8	7x 7 x 7	.21	5.7
1/2	7x 7 x 7	.37	9.75
5/8	7x 7 x 7	.58	14.6
3/4	7x 7 x 19	.88	21.4
7/8	7x 7 x 19	1.19	28.4
1	7x 7 x 19	1.56	36.2
1.1/8	7x 7 x 19	1.94	44.7
1.1/4	7x 7 x 19	2.39	53.7



Read important warnings and information preceding wire rope section *Listed for comparison only. Actual operating loads may vary, but should never exceed recommended design factor or 20% of catalog Breaking Strength.

WWW.CCBM.MX VENTAS@CCBM.MX +52 1 833227 8507